

## Description

The 8481 *Premium Carbon Conductive Grease* is an electrically conductive grease with a synthetic oil base. This product is similar to the MG 846 silicone conductive grease, but unlike its silicone counterpart the 8481 synthetic-oil grease is essentially non-bleeding. Further, it includes corrosion inhibitors that provide superior corrosion resistance.

The 8481 grease lubricates and improves electrical connections between sliding surfaces and parts, ensuring good grounding connection. It is also used to improve electrical continuity between irregular and pitted surfaces, as well as providing an economical way to protect switches against corrosion.

## Benefits & Features

- Improves electrical connections between irregular surfaces.
- Resistivity better than 400 Ω
- Extends the life of contacts
- Silicone Free
- Safe on plastics

## Application and Storage Conditions

<i>Properties</i>	<i>Value</i>
Shelf Life	5 year
Storage Temperature Limits	-10 to +40 °C [14 to +104°F]

## Temperature Service Ranges

<i>Properties</i>	<i>Value</i>
Service Temperature	-68 to +165 °C [-90 to +329 °F]
Maximum coverage for 25 µm [1.0 mil] thickness <sup>a)</sup>	<180 000 cm <sup>2</sup> [<190 ft <sup>2</sup> ]

a) Theoretical coverage per 454 mL [1 pint] assuming 100% transfer efficiency.

## Properties

<i>Conductivity Properties</i>	<i>Method</i>	<i>Value</i>
Resistivity	2 point	<400 Ω
Volume resistivity( $\rho_v$ )		<i>test in progress</i>
Volume Conductivity ( $\sigma_v$ )		"
Thermal Conductivity @25 °C	ASTM E 1461	0.288 W/(m·K)

*Continued on the next page*



ISO 9001 Registered Quality System.  
Burlington, Ontario, Canada QMI File # 004008

# Premium Carbon Conductive Grease 8481 Technical Data Sheet

8481

<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Color		Black
Odor		Odorless
Density @25 °C		1.03 g/mL
Viscosity @25 °C [77 °F] <sup>a)</sup>		630,000 cP [615,000 cSt]
Drop Point	ASTM D 2265	300°C [572 °F]
Cone Penetration	ASTM D 217	<i>test in progress</i>
Oil Separation (Boeing test) <sup>b)</sup>		Slight oil separation
Corrosivity		Non-Corrosive
%Filler		15%
%Evaporation loss @ 25 °C, 44 h		0.6% (wt)
VOC (Volatile Organic Compound) <sup>c)</sup>	Calculated	5%
Lubricant		Yes
Bleed Resistant		Yes

- a) Brookfield viscometer @ 6 rpm with spindle RV # 7  
 b) After ten cycles from -40 °C to 121 °C.  
 c) According to WHIMS regulation

<i>Synthetic Oil Properties</i>	<i>Method</i>	<i>Value</i>
Oil viscosity index <sup>a)</sup>	ASTM D 2270	>110
Fire Point <sup>b)</sup>	ASTM D 92	321 °C [559 °F]
Flash Point C.O.C.	ASTM D 92	>290 °C [550 °F]

*Note:* Values based on synthetic oil component only.

- a) High oil viscosity index of more than a 100 indicate small oil viscosity change with temperature.  
 b) Temperature at which oil will continue to burn for at least 5 s after ignition with an open flame.

## Storage

Store between -10 °C and +40 °C [14°F and 104 °F] in dry area.

## Health, Safety, and Environmental Awareness

Please see the 8481 **Material Safety Data Sheet** (MSDS) for greater details on transportation, storage, handling and other security guidelines.


**Environmental Impact:** The volatile organic content is 5% by WHMIS and European standards. Not regulated as a dangerous good for transport.

**Health and Safety:** Wear safety glasses and disposable gloves to avoid exposures.

### HMIS® RATING

HEALTH:	1
FLAMMABILITY:	1
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

### NFPA® 704 CODES



*Approximate HMIS and NFPA Risk Ratings Legend:*

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

## Application Instructions

The conductive grease performance depends on mainly on surface preparation. Improperly prepared contact surfaces can degrade the paste's stability, conductivity, and lubrication characteristics. While the thickness and coverage are also important, the application method itself can easily be adjusted according to performance and application needs.

### Prerequisites

- Wear gloves and protective clothing (See 8481 MSDS). This product is messy.
- Clean and dry the surface of the substrate to remove other oils and greases, as well as dust, water, solvents, or any other contaminants.

*Recommendations:* Use MG 401B Nutrol Control Cleaner or MG 824 Isopropyl Alcohol

### Equipment

- Lint free cloth (for cleaning contact and for wiping excess residue)
- Spatula or stick application tools (sized appropriately for your application).
- Isopropyl alcohol or other residue-free organic solvents.

**NOTE:** Avoid oil-based cleaners (like WD-40) that are designed to leave a film on the metal surface. Contaminant oil or grease films may act like barriers reducing the electrical contact between the conductive paste and the metallic substrate.

### To apply the grease

1. Wipe the contact with a lint-free cloth
2. Clean the contacts with isopropyl alcohol or other non-oil based cleaner.
3. Once dry, apply the paste with the application tool to the contact, ensuring adequate coverage and desired thickness.

## **ATTENTION!**

- DO NOT apply or smooth grease with bare finger. Carbon black grease is hard to clean and may transfer to other surfaces by touch. Further, you may introduce contaminants that degrade the overall performance of the grease.

## **Packaging and Supporting Products**

<i>Cat. No.</i>	<i>Form</i>	<i>Net Volume</i>	<i>Net Weight</i>	<i>Shipping Weight</i>
<b>8481-80G</b>	Grease	73 mL 2.5 fl oz	0.08 kg 0.17 lb	0.7 kg <sup>a)</sup> 1.5lb <sup>a)</sup>
<b>8481-1P</b>	Grease	454 mL 1 pint	0.5 kg 1.1 lb	0.55 kg 1.2 lb

a) Pack of 6 tubes

## **Technical Support**

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at [www.mgchemicals.com](http://www.mgchemicals.com).

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: 1-800-340-0772 Ext. 1030 (Canada, Mexico & USA)

1-905-331-1396 Ext. 1030 (International)

Fax: 1-905-331-2862 or 1-800-340-0773

Mailing address: **Manufacturing & Support**  
1210 Corporate Drive  
Burlington, Ontario, Canada  
L7L 5R6

**Head Office**  
9347–193rd Street  
Surrey, British Columbia, Canada  
V4N 4E7

## **Warranty**

*M.G. Chemicals Ltd.* warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

## **Disclaimer**

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.